

**Physical Properties  
for Grout**

Date : 27-07-2006  
Client : Prokem Co.  
Plant Location : Live F.F  
Testing Material : Kemcrete 101  
Client Reference : QX 55

Delivery Date : 12-07-2006

**Compressive Strength :**

		7 Days		
		1	2	3
Date of Casting		19-7-06		
Date of Testing		26-7-06		
Dimension of mold	( mm )	50	50	50
Crushing Load	( KN. )	101.3	100.1	98.4
Strength	N/mm <sup>2</sup>	40.5	40.0	39.4
Average	N/mm <sup>2</sup>	40.0		

**Remarks :**

\* Mix Composition

One Bag Kemcrete 101 (25 Kg) + 2.0 Liter Water + .008LMCI

**Tested By :**

**Checked By :**

