



20 haron st. Dokki Giza Arab Republic Of Egypt

Phone : (02)7485199 – 7488164 – 7492276 – 3368891

28 Essam Helmy El-Masry Semoha Tel. : 4260288

شارع مارون-الدقي-الجيزة ج.م.ع

هاتف : ٣٣٦٨٨٩١-٧٤٩٢٢٧٦-٧٤٨٨١٦٤-٧٤٨٥١٩٩

٢٨ - شارع عصام حلمي المصري - سموحة ت : ٤٢٦٠٢٨٨

**Physical Properties
for Grout**

Date : 17/12/2005
Client : Prokem Co.
Plant Location :
Testing Material : Kemfloor ESL grey
Client Referance : QX 55

Delivery Date : 12/12/2005

Compressive Strength :

7 Days

| | | 1 | 2 | 3 |
|---------------------|-----------------------|----------|-------|-------|
| Date of Casting | | 8/12/05 | | |
| Date of Testing | | 15/12/05 | | |
| Dimension of mold | (mm) | 70 | 70 | 70 |
| Weight of sample | gm | 791 | 782 | 788 |
| Density of Concrete | (gm/cm ³) | 2.306 | 2.280 | 2.297 |
| Crushing Load | (KN.) | 218.8 | 223.3 | 228.2 |
| Strength | Kg/cm ² | 455.2 | 464.5 | 474.7 |
| Average | Kg/cm ² | | 464.8 | |

Remarks :

* Sampled & Casted by the Client

Tested By :

