

Kemrepair 2F

High Strength Fiber Polymer Modified Non-Shrink Two Component Repair Mortar

Description	Kemrepair 2F is a high strength ,non-shrink , two component patching cementitious mortar especially designed for repairing of vertical and horizontal surfaces of concrete and masonry, fortified with special alkali resistant fiber, that improve appreciably the impact, flexural & tensile strength
Where to use	Kemrepair 2F is used for general repair purposes of damaged or spelled concrete, for the protection of steel reinforcement rods against corrosion, repairs honeycombs, cracks and fissures Kemrepair 2F is used: • For restoration of concrete structures that permanently subjected to severe weathering conditions • As a sealer and bonding mortar between two layers of concrete to solve the problem of cold joints • For restoration of lines and shapes of permanently subjected to severe weathering conditions • For restoration of lines and shapes of damaged pre-fabricated concrete elements • For non-slip ramp constructions, as it is resistant to traffic wear
Advantages	Kemrepair 2F provides the following advantages: • Easy to use • Excellent weathering resistance • Rust inhibiting properties since it does not contain calcium chloride • Very good thixotropic without slump or the need for using form work • Excellent adhesion to concrete and steel • Non-shrink, non-toxic & non-flammable • High mechanical strengths • Can be used for filling voids or holes in floors • Reduces rate of carbon dioxide & chlorides
Properties	
Mechanical Properties:	After 28 days cured at 20 °C and R.H. of 70 ±5%
Compressive Strength	40 - 50 N/mm ²
Flexural Strength	5 - 7 N/mm ²
E- Modules	20000 N/mm ²
Adhesion strength to concrete	>1.5 N/mm ²
Adhesion strength to plain bars	3.5 N/mm ²
Adhesion strength to deformed bars	9 N/mm ²
Pot life	30 minutes
Physical Properties:	
Color	Grey
Setting time	Initial: 180 minute Final: 250 minute
Density	2 ±0.2 gm. /cm ³ Fresh wet

Surface Preparation	• Remove all damaged and contaminated concrete to reach the sound core • Remove additional concrete surrounding and along the reinforcement bars • Formation of clean-cut edges to avoid feather edges • Thoroughly clean reinforcement bars to remove all rust, scale and surface contaminants (Sand or abrasive blasting is advised.) • If steel is heavily corroded that significant loss of section has occurred, add new steel (Please consult a qualified engineer.) • Clean and dampen the concrete surface with water, or use Kembond SBR as a bonding agent between the old and the new layer • Rebar's can be primed with Kemprim ZRS for protection against corrosion
Expansion Joints	Shall be installed in accordance with local building codes & never bridge an expansion, contraction, or construction joint
Mixing	Mix Kemrepair 2F powder with mixing liquid to a batter consistency
Application	• Apply a slurry coat by brush over reinforcing rods and concrete • Slush mix under and between steel rods and make sure all cracks and voids are filled • Reinforcing rods should be completely surrounded by Kemrepair 2F in order to avoid corrosion • Then mix Kemrepair 2F to a thicker consistency and apply successive layers of 20 -25 mm • Minimum layer thickness 10 mm • Scratch each layer before applying the next in order to improve the bonding • Each new layer should be applied within 1-2 hour • Remodel to the original profile • Curing: • On completion of the repairing operation, exposed areas which are not to be cut back should be thoroughly cured by means of water application, Kemcure curing membrane or wet hessian for at least 48 hours
Cleaning	Kemrepair 2F should be removed from tools and equipment immediately after use with clean water
Theoretical coverage	2 Kg/m ² /1mm thick
Packaging	20 kg Sacks + 5 Kg Liquid Polymer
Shelf life & Storage	Kemrepair has a shelf life of 12 months if maintained in dry storage conditions, away from sunlight
Precaution	• Do not add any water • In case retarded drying out is required, apply a curing agent or cementitious paint immediately after application • Kemrepair 2F should not be applied to substrates that is exposed to running water or which are permanently wet • Application should not be carried out when ambient temperature is below 5 °C • Kemrepair 2F should not be applied in thickness less than 10mm or width less than 55mm
Health and Safety	• Kemrepair 2F is non-toxic if come in contact with skin • Use gloves to avoid contact with skins • If skin comes in contact, wash immediately with soap and water • Do not use solvents • Eye contamination must be immediately washed with water, then seek medical treatment • Do not breath dust, Use a practical mask
Additional Information	PROKEM provides the construction industry with a comprehensive range of construction chemicals and specialty products answering the queries of modern engineers for trouble-free durable structures PROKEM designs tailor-made products should there be a critical application that requires specific properties rather than our main range for our customer's satisfaction PROKEM reserves the right to change the properties of its products All orders are accepted subject to our current terms of sale & delivery Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request PROKEM extends technical services to include after-sales support to assist users in the proper handling of our products